

Part/Assembly	MAJOR DAMAGE	MINOR DAMAGE
	REMOVE FROM SERVICE IF THE DAMAGE EXCEEDS THE BELOW LIMIT	INSPECT NEXT INTERVAL; REPAIR AT OPERATOR'S DISCRETION
Body Panels (continued)	<p>The combined size of multiple damaged areas on any one panel, with the exception of the Top Panel, exceeding 25% of the total panel surface area. (See Table 1).</p> <p>Top panel combined size of single or multiple damaged areas not to exceed 5% of total panel surface area. (See Table 1)</p> <p>Any 2 holes or group of holes separated by less than 3 inches (7.6 cm) of undamaged panel will be classified as a single damage area and may not exceed 12 inches (30.5 cm) in any dimension (10 inches on the Top Panel).</p> <p>Deformation:</p> <p>The inward buckling of panels more than 1 inch (2.5 cm) from original profile.</p> <p>The outward buckling of panels more than ½ inch (1.3 cm) from original profile.</p> <p>Cracks:</p> <p>A crack that exceeds 12 inches on both sides of the panel. (A crack is defined as a complete break of fiber on both sides of panel. It is common for the panel to turn white after severe impact. This is not a crack unless the skin material is completely broken through.)</p>	<p>NA</p> <p>NA</p> <p>NA</p> <p>NA</p> <p>NA</p> <p>Any crack less than 12 inches on both sides of the panel or any size crack present on one side of the panel is considered minor damage.</p>